

Nox-Rust® 1100 VCI Liquid
Nox-Rust® 1101 VCI liquid
concentrate



Product Description

Nox-Rust® 1100 is a volatile corrosion inhibitive lubricating liquid for use in the preservation of ferrous and/or other metal parts in enclosed systems. By combining the protective properties of preservative oil with Daubert VCI® proprietary volatile corrosion inhibitors (VCI), Nox-Rust 1100 liquid provides long-term protection against rust in closed systems or voids.

Typical examples of closed systems include fuel tanks, storage tanks cylinders, transmissions, hydraulic and coolant circulating systems. It may also be fogged into shipping cases to protect unpainted auto and truck body sections during shipments. It can also be used for winter lay-up of farm and road building equipment and for summer storage of school buses, snowplows, snowmobiles, etc.

Conventional lubricating or preservative liquids slushed or fogged into such systems will drain away from the vertical metal surfaces in about six months, exposing the metal to moisture, condensation and corrosion. While Nox-Rust 1100 also drains away, the vaporizing rust inhibitors evolving from the product spread throughout the voids of system and neutralize the corrosion-causing tendency of the moisture in the air. Nox-Rust 1100, being highly fortified with contact inhibitors, also protects the metal below the oil level.

Physical Properties

(Typical values, not specifications)

Appearance:	Light golden oil
Viscosity:	210 cps
Carrier:	Oil
Coverage:	800 sq. ft. per gal.
Film type:	Oily
Volatile:	5%
Film thickness:	0.2 mils
Specific gravity:	0.900
Freezing point:	NA
Flash point:	225° F min.
Odor:	Slight
Accelerated Corrosion Test Humidity JAN-H-792, 100% RH @ 120 F	300 hours
Vapor phase Protection, Mil-P-46002A	
Procedure:	Pass
Removal:	Not necessary

Packaging and Storage

Nox-Rust 1100 is available in conveniently sized 5 gal (18.9 l) pails and 55 gal (208 l) drums.

Store sealed, in a dry location, out of direct sunlight in temperatures not to exceed 100°F (40°C) or below 40°F (5°C). For best results, use within 1 year after date of manufacture.

Typical Applications and Use

Nox-Rust 1100 liquid is ready to use in systems where a combination of metals are present, including steel, iron, zinc, copper, brass, and aluminum.

- In drive clutch and steering clutch assemblies, which are subject to corrosion during shipment and storage, fog 3 oz. of Nox-Rust 1100 to the hydraulic test oil. After testing, add an additional 3 oz.
- For carburetor engines:
 - Crankcase, including crankshaft, bearings, rocker arms and surfaces normally lubricated by crankcase oil, use

- 1 oz. per quart of crankcase oil,
or 1% by volume.
- For fuel tanks, use 2 oz. per
gallon on tank volume.
- Oil bath cleaner, use 1/3 oz. per
engine cylinder.
- For diesel engines, use same amount
as carburetor engines and
 - Injection pumps, add ½ oz. per
engine cylinder.
 - Fuel tanks, fog 1 oz. per each
7½ gallons (1 cu. ft.) capacity. If
tank contains oil or gasoline,
add 1 oz. for each gallon
present.
- For transmissions, add 2% Nox-Rust
1100 to the lubricant.

Nox-Rust® 1101 VCI liquid concentrate is
about a 2:1 concentrated version of Nox-
Rust® 1100.

® Registered trademark of Daubert VCI, Inc.
Nox-Rust 1100 Product Data.doc Rev.0 05/03

©2003 Daubert VCI, Inc.

The data, statements and recommendations in this product information sheet are based on testing, research and other development work, which has been carefully conducted by us, and we believe such data, statements and recommendations will serve as reliable guidelines. Physical properties shown above represent typical values and are not intended for use in writing specifications. However, this product is subject to numerous uses under varying conditions over which we have no control, and accordingly, we do NOT warrant that this product is suitable for any particular use. Users are advised to test the product in advance to make certain it is suitable for their particular production conditions and use. All products manufactured by us are warranted to be first class material and free from defects in material and workmanship. Liability under this warranty is limited to the net purchase price of any such products proven defective or, at our option, to the repair or replacement of said products upon their return to us transportation prepaid. All claims on defective products must be made in writing within 30 days after the receipt of such products in your plant and prior to further processing or combining with other material and products.

WE MAKE NO WARRANTY, EXPRESS OR IMPLIED, AS TO THE SUITABILITY OF ANY OF OUR PRODUCTS FOR ANY PARTICULAR USE, AND WE SHALL NOT BE SUBJECT TO LIABILITY FROM ANY DAMAGES RESULTING FROM THEIR USE IN OPERATIONS NOT UNDER OUR DIRECT CONTROL.

THIS WARRANTY IS EXCLUSIVE OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, AND NO REPRESENTATIVE OF OURS OR ANY OTHER PERSON IS AUTHORIZED TO ASSUME FOR US ANY OTHER LIABILITY IN CONNECTION WITH THE SALE OF OUR PRODUCTS.